

# DMEGC

-----横店东磁-----

## 永磁铁氧体特性标准 Feature Distribution Chart of Hard Ferrite

材料牌号 Material Grade	剩余磁通密度 Br Residual Flux Density		磁感应矫顽力 Hcb Coercive Force		内禀矫顽力 Hcj Intrinsic Coercive Force		最大磁能积(BH)max Max. Energy product	
	mT	Gs	kA/m	Oe	kA/m	Oe	kJ/m <sup>3</sup>	MGOe
	DM10T	210-240	2100-2400	127-159	1600-2000	211-279	2650-3500	6.4-9.5
DM25	380-400	3800-4000	143-175	1800-2200	147-179	1850-2250	25.5-29.6	3.2-3.7
DM30	390-410	3900-4100	175-207	2200-2600	179-211	2250-2650	27.1-31.2	3.4-3.9
DM33H	390-410	3900-4100	239-271	3000-3400	243-275	3050-3450	27.1-31.2	3.4-3.9
DM34H	370-390	3700-3900	263-291	3300-3650	304-330	3850-4150	24.7-28.7	3.1-3.6
DM3845	370-390	3700-3900	263-299	3300-3750	342-378	4300-4750	25.5-28.7	3.2-3.6
DM3850	370-390	3700-3900	267-303	3350-3800	382-406	4800-5100	25.5-28.7	3.2-3.6
DM4036	395-415	3950-4150	263-291	3300-3650	279-303	3500-3800	28.7-31.8	3.6-4.0
DM4040	390-410	3900-4100	271-295	3350-3700	307-326	3850-4100	28.7-31.8	3.6-4.0
DM4045	390-410	3900-4100	287-310	3600-3900	358-382	4500-4800	28.7-31.8	3.6-4.0
DM4129	400-420	4000-4200	215-239	2700-3000	219-243	2750-3050	29.6-32.8	3.7-4.1
DM4229	415-435	4150-4350	215-239	2700-3000	219-243	2750-3050	30.3-33.4	3.8-4.2
DM4240	410-430	4100-4300	283-307	3550-3850	307-330	3850-4150	31.2-35.2	3.9-4.4
DM4350	420-440	4200-4400	294-326	3700-4100	386-410	4850-5150	33.4-36.6	4.2-4.6
DM4433	430-450	4300-4500	247-271	3100-3400	251-275	3150-3450	33.4-36.6	4.2-4.6
DM4545	440-460	4400-4600	318-350	4000-4400	347-370	4350-4650	36.6-39.8	4.6-5.0
DM4550	440-460	4400-4600	303-334	3800-4200	374-406	4700-5100	36.6-39.8	4.6-5.0
DM4636	450-470	4500-4700	255-279	3200-3500	275-299	3450-3750	38.3-41.5	4.8-5.2
DM4654	450-470	4500-4700	330-356	4150-4450	415-445	5250-5650	39.8-43.0	5.0-5.4
DM4748	460-480	4600-4800	328-352	4150-4400	368-392	4650-4950	41.4-44.6	5.2-5.6

注：判定时以国际单位制的标准值为依据